

BISCO® Silicones



BISCO® RS-770

Continuous Roll Closed-Cell Silicone Sponge – Data Sheet

TEST METHOD	TYPICAL PROPERTIES
ASTM D 3574	465 (29)
	2.4 – 12.7 (0.094 - 0.500)
ASTM D 1056	82 - 138 (12 - 20)
ASTM D 1056 22 hours @ 100°C, 50% compressed, 24 hours recovery	<15
ASTM D 412	0.76 (110)
ASTM D 412	130
ASTM D 1056	<3
Water pressure: 10.3 kPa (1.5 psi) Gasket width: 6.34 mm (0.250") Compression: 30% Gasket thickness: 3.175 mm (0.125")	No Leakage
	Charcoal Gray
	205℃ (401°F)
	260°C (500°F)
ASTM D 746	-55°C (-67°F)
ASTM C 518	0.08 (0.57)
FMVSS 302	2.4 (0.094)
	AMS 3196
Gaskets & Seals JMLU2	UL50, UL50E, UL508 & UL157
	274 (2)
	±0.51 (±0.020)
	<u>±</u> 1.14 (<u>±</u> 0.045) <u>±</u> 1.49 (<u>±</u> 0.059)
	ASTM D 1056 ASTM D 1056 22 hours @ 100°C, 50% compressed, 24 hours recovery ASTM D 412 ASTM D 412 ASTM D 1056 Water pressure: 10.3 kPa (1.5 psi) Gasket width: 6.34 mm (0.250") Compression: 30% Gasket thickness: 3.175 mm (0.125") ASTM D 746 ASTM C 518

¹Typical values are a representation of an average property value of a given population of the product.

Rogers Corporation Elastomeric Material Solutions US 800.935.2940 | Europe +32.9.235.36.11 | Asia +86.512.6258.2700

The information contained in this Data sheet is intended to assist you in designing with Rogers' BISCO Silicone foam materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' BISCO Silicone foam materials for each application. The Rogers logo, Helping Power, protect, connect our world and BISCO are trademarks of Rogers Corporation or one of its subsidiaries. ©2016 Rogers Corporation, All rights reserved. Printed in U.S.A. 0216-PDF. Publication #180-312

Typical properties are based on 6.35mm (0.250") sample.

For specification values, please contact Rogers Corporation.